

Protectosil® 100

Protectosil® 100 is a free-flowing, colorless, frost resistant, solvent-free liquid based on a monomeric silane

Technical Data

Properties and test methods	Value	Unit	Method
Appearance	free-flowing, colorless liquid	-	-
Solvent	solvent-free	-	-
Strength	98-100	%	-
Odor	fruity	-	-
Density (20 °C)	0.93	g/cm ³	DIN 51757
Boiling point	approx. 150	°C	DIN 51751
Viscosity	approx. 0.8	mPa·s	DIN 53015
Flash point	39	°C	DIN 51755

Registration

Protectosil® 100

EINECS/ELINCS (EU):	Yes
AICS (Australia):	Yes
DSL/NDSL (Canada):	Yes
PICCS (Philippines):	Yes
TSCA (USA):	Yes
IECSC (P.R. China):	Yes
ENCS (Japan):	Yes
ECL (South Korea):	Yes

Protectosil® 100 is a free-flowing, colorless, frost resistant, solvent-free liquid based on a monomeric silane.

It is specifically intended for the water-repellent treatment of mineral construction materials in outdoor areas. The water vapor permeable impregnation effectively prevents the penetration of water and dissolved damage-causing salts, such as chlorides. **Protectosil® 100** seals hairline cracks of up to 0.3 mm.

Areas of Application

For waterproofing mineral substrates, in particular low-porosity substrates such as concrete (road bridges, port installations marine concrete structures, concrete facades, exposed aggregate concrete), clinker masonry and ceramic tiles as well as waterproofing under coating systems.

Safety and Handling

Before considering the use of Dynasylan® and Protectosil® products please read its Material Safety Data sheet (MSDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Material Safety Data Sheet is available after registration on our website www.dynasylan.com or upon request from your local representative, customer service or from Evonik Industries AG, Product Safety Department, E-MAIL sds-im@evonik.com.

Packaging and Storage

Protectosil® 100 has a shelf life of more than 18 months if stored in originally sealed containers. Containers must be kept tightly sealed and protected from moisture. **Protectosil® 100** is supplied in 26,5 l and 193,5 l drums.

Properties and Use

The substrates to be treated should be air-dry and clean in order to ensure deep penetration of the active ingredient. During application the outside temperature and the temperature of the substrate should be within the range from 0 °C to 45 °C. The material should not be applied if there is strong wind or if it is raining. The material must not come into contact with water either before or during use.

Protectosil® 100 must be applied by flowcoating to the saturation point. This is achieved by allowing it to flow without pressure against the surface to be treated. All liquid delivery devices are suitable (airless sprayguns, for example). The material must not be atomized or applied with a brush.

Protectosil® 100 must remain in contact with the substrate for several seconds as a liquid film. Horizontal surfaces should have a shiny, wet appearance for 3-5 seconds. Vertical surfaces should exhibit a 30-50 cm shiny curtain of liquid. All equipment and containers must be clean and dry. After use they can be cleaned with any organic solvent (methylated spirit, petrol or thinners).

Non-absorbent substrates such as glass, wood, plastic, and metal cannot be treated with **Protectosil® 100**. In the worst case, product not absorbed by the substrate may react with atmospheric moisture to form a greasy, glossy silicone resin film. Substrates such as those mentioned above should therefore be covered before the application. If they nevertheless become contaminated, the resulting film can be easily removed if cleaned immediately using conventional cleaning agents, or alcohol (spirit of soap) in difficult cases.

Glass, wood and metal are not attacked by **Protectosil® 100**. Neither are most plastics used in construction. If in doubt, carry out a preliminary test.

Plants in the vicinity of the substrate to be treated should be protected against contact with **Protectosil® 100**.

Application

Mixing recommendation

Protectosil® 100 can also be used in diluted form. We recommend using a 40 % solution of the active ingredient in anhydrous (absolute) ethanol.

Pour four parts by volume **Protectosil® 100** into a clean container and mix with six parts by volume anhydrous (absolute) ethanol. Stir briefly. The solution is now ready for use.

A diluted ethanol-based solution is suitable particularly for waterproofing absorbent mineral facade construction materials such as

- brickwork
- slightly absorbent clinker masonry
- exposed-aggregate concrete
- mineral plaster facades
- sand-lime brickwork
- autoclaved aerated concrete.

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. EVONIK DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, AND SHALL HAVE NO LIABILITY FOR, MERCHANTABILITY OF THE PRODUCT OR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE), OR OTHERWISE. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

Europe / Middle-East / Africa / Row

Evonik Industries AG

Inorganic Materials
Rodenbacher Chaussee 4
63457 Hanau-Wolfgang
Germany
PHONE +49 6181 59 13636
FAX +49 6181 59 13737
protectosil@evonik.com
www.protectosil.com

Asia / Pacific

Evonik Degussa (SEA) Pte. Ltd.

Inorganic Materials
3 Internatioanl Business Park
#07-18, Nordic European Centre
Singapore 609927
PHONE +65 6890 6830
FAX +65 6899 6630
protectosil@evonik.com
www.protectosil.com

Asia / Pacific

Evonik Taiwan Ltd.

Inorganic Materials
Artist Construction Bldg
9F, No. 133
Min Sheng East Road, Sec 3
Taipei, 105 Taiwan, R.O.C.
Taiwan
PHONE +886 227 17 1242
FAX +886 227 17 2106
protectosil@evonik.com
www.protectosil.com

North America

Evonik Degussa Corporation

Inorganic Materials
P.O. Box 677
299 Jefferson Road
Parsippany, NJ 07054-0677
USA
PHONE (TOLL FREE) +1 800 828 0919
PHONE +1 973 929 8513
FAX +1 973 929 8503
protectosil@evonik.com
www.protectosil.com

Asia / Pacific

Evonik Degussa (Shanghai) Co. Ltd.

Inorganic Materials
55, Chungdong Road
Shanghai 201108
P.R. China
PHONE +86 21 6119 1053
FAX +86 21 6119 1075
protectosil@evonik.com
www.protectosil.com

Asia / Pacific

Evonik Japan Co. Ltd

Inorganic Materials
12th Floor Monolith Building
2-3-1, Nishi-Shinjuku-ku
Tokyo 163-0912
Japan
PHONE +81 353 23 7300
FAX +81 353 23 7399
protectosil@evonik.com
www.protectosil.com

Latin America

Evonik Brasil Ltda.

Inorganic Materials
Alameda Campinas, 579
01404-000 São Paulo-SP
Brazil
PHONE +55 11 3146 4123
FAX +55 11 3146 4148
protectosil@evonik.com
www.protectosil.com

Asia / Pacific

Evonik Korea Ltd.

Inorganic Materials
94, Galsan 1-dong
Bupyeong-gu
Incheon, 403-081, Korea
PHONE +82 32 510 2433
FAX +82 32 505 2510
protectosil@evonik.com
www.protectosil.com

Asia / Pacific

Evonik India Pvt. Ltd.

Inorganic Materials
Krislon House
Saki Vihar Road, Anderi (E)
Mumbai - 400 072
India
PHONE +91 226 7238 809
FAX +91 226 7238 811
protectosil@evonik.com
www.protectosil.com