

Protectosil® PROFICLEAN GEL

Graffiti-Cleaner for Protectosil ANTIGRAFFITI® treated porous mineral surfaces

Technical Data

Properties and test methods	Value	Unit	Method
Density	0,971	g/cm ³	DIN 51757
Smell	lemon like	-	-
pH-value	4,2	-	DIN 53015
Appearance	milky, viscous	-	-
Flash point	approx. 19	°C	DIN 51755
Boiling point	112	°C	DIN 51751

Registration

Protectosil® PROFICLEAN GEL

EINECS/ELINCS (EU):	Yes
AICS (Australia):	Yes
DSL/NDSL (Canada):	Yes
PICCS (Philippines):	Yes
TSCA (USA):	Yes
IECSC (P.R. China):	Yes
ENCS (Japan):	Yes
ECL (South Korea):	Yes

Protectosil® PROFICLEAN GEL is a very effective graffiti cleaner.

The product has a lemon like smell. The cleaner is particularly designed for surfaces which have been treated with **Protectosil®** ANTIGRAFFITI. Spray colors, laquers, felt-tip or ball pen scribbling can be easily removed using **Protectosil®** PROFICLEAN GEL.

Safety and Handling

Before considering the use of Dynasylan® and Protectosil® products please read its Material Safety Data sheet (MSDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Material Safety Data Sheet is available after registration on our website www.dynasylan.com or upon request from your local representative, customer service or from Evonik Industries AG, Product Safety Department, E-MAIL sds-im@evonik.com.

Packaging and Storage

Protectosil® PROFICLEAN GEL has a shelf life in properly sealed containers of more than one year. The product should be stored at temperatures between 0 °C and 40 °C. **Protectosil®** PROFICLEAN GEL is supplied in 25 l and 200 l drums.

Properties and Use

Protectosil® PROFICLEAN GEL should only be applied to dry surfaces. **Protectosil®** PROFICLEAN GEL should be homogeneously spreaded to the surfaces using a soft roller or brush (e.g. wallbrush or paint brush).

The temperature during application should be between 0 °C and 40 °C. The cleaner should interact with the paint for about 15-30 minutes. Never let the cleaner dry on the surface. After applying about 400 g/m² of cleaner, it should be thoroughly distributed over the paint and the substrate surface. It might be necessary to apply additional fresh cleaner. After the paints are dissolved they can be washed away by a high-pressure cleaner (with max. 12 bar). The described procedure should be carried out twice. If the surface had been attacked by paints based on bitumen, additional use of a special bitumen cleaner might be necessary.

In case of painted surfaces, such as window frames or other metal pieces, care has to be taken when applying the cleaner. It is recommended to do test patches in order to avoid unwanted side effects.

Important: **Protectosil®** PROFICLEAN GEL should not be sprayed on spots created with permanent markers. In this case it is recommended to apply the cleaner on a towel, wiping off the spots. Before applying **Protectosil®** PROFICLEAN GEL please shake the drum thoroughly.

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. EVONIK DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, AND SHALL HAVE NO LIABILITY FOR, MERCHANTABILITY OF THE PRODUCT OR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE), OR OTHERWISE. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

Europe / Middle-East / Africa / Row

Evonik Industries AG

Inorganic Materials
Rodenbacher Chaussee 4
63457 Hanau-Wolfgang
Germany
PHONE +49 6181 59 13636
FAX +49 6181 59 13737
protectosil@evonik.com
www.protectosil.com

Asia / Pacific

Evonik Degussa (SEA) Pte. Ltd.

Inorganic Materials
3 Internatioanl Business Park
#07-18, Nordic European Centre
Singapore 609927
PHONE +65 6890 6830
FAX +65 6899 6630
protectosil@evonik.com
www.protectosil.com

Asia / Pacific

Evonik Taiwan Ltd.

Inorganic Materials
Artist Construction Bldg
9F, No. 133
Min Sheng East Road, Sec 3
Taipei, 105 Taiwan, R.O.C.
Taiwan
PHONE +886 227 17 1242
FAX +886 227 17 2106
protectosil@evonik.com
www.protectosil.com

North America

Evonik Degussa Corporation

Inorganic Materials
P.O. Box 677
299 Jefferson Road
Parsippany, NJ 07054-0677
USA
PHONE (TOLL FREE) +1 800 828 0919
PHONE +1 973 929 8513
FAX +1 973 929 8503
protectosil@evonik.com
www.protectosil.com

Asia / Pacific

Evonik Degussa (Shanghai) Co. Ltd.

Inorganic Materials
55, Chungdong Road
Shanghai 201108
P.R. China
PHONE +86 21 6119 1053
FAX +86 21 6119 1075
protectosil@evonik.com
www.protectosil.com

Asia / Pacific

Evonik Japan Co. Ltd

Inorganic Materials
12th Floor Monolith Building
2-3-1, Nishi-Shinjuku-ku
Tokyo 163-0912
Japan
PHONE +81 353 23 7300
FAX +81 353 23 7399
protectosil@evonik.com
www.protectosil.com

Latin America

Evonik Brasil Ltda.

Inorganic Materials
Alameda Campinas, 579
01404-000 São Paulo-SP
Brazil
PHONE +55 11 3146 4123
FAX +55 11 3146 4148
protectosil@evonik.com
www.protectosil.com

Asia / Pacific

Evonik Korea Ltd.

Inorganic Materials
94, Galsan 1-dong
Bupyeong-gu
Incheon, 403-081, Korea
PHONE +82 32 510 2433
FAX +82 32 505 2510
protectosil@evonik.com
www.protectosil.com

Asia / Pacific

Evonik India Pvt. Ltd.

Inorganic Materials
Krislon House
Saki Vihar Road, Anderi (E)
Mumbai - 400 072
India
PHONE +91 226 7238 809
FAX +91 226 7238 811
protectosil@evonik.com
www.protectosil.com