

Protectosil® 100 NK

Water repellent formulation with water beading effect for mineral and hydroxyl-group containing substrates

Technical Data

Properties and test methods	Value	Unit	Method
Density	approx. 0.88	g/cm ³	DIN 51757
Boiling point	175 - 186	°C	DIN 51751
Flash point	> 57	°C	DIN 51755
Active ingredient content	97 - 100	%	-

Registration

Protectosil® 100 NK

AICS (Australia):	Yes
DSL/NDSL (Canada):	No
PICCS (Philippines):	Yes
TSCA (USA):	Yes
IECS (P.R. China):	Yes
ENCS (Japan):	Yes
ECL (South Korea):	No
EINECS/ELINCS (EU):	Yes

Protectosil® 100 NK is suitable for waterproofing porous mineral building materials, glass, cotton, cellulose, wood, etc.

An excellent beading effect develops on suitable substrates only a short time after application.

Protectosil® 100 NK can be applied at full-strength or after dilution with suitable solvents.

Safety and Handling

Before considering the use of Dynasytan® and Protectosil® products please read its Material Safety Data sheet (MSDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Material Safety Data Sheet is available after registration on our website www.dynasytan.com or upon request from your local representative, customer service or from Evonik Industries AG, Product Safety Department, E-MAIL sds-im@evonik.com.

Packaging and Storage

Protectosil® 100 NK can be stored in originally sealed containers without any deterioration in quality for at least 6 months. The storage temperature are between -10 °C and 40 °C. **Protectosil® 100 NK** is available in 25 l, 200 l and 1.000 l.

Properties and Use

Suitable solvents:

- Ethanol* (water free, denatured with petroleum hydrocarbons)
- Aliphatic hydrocarbon solvents (pentane, hexane, heptane, etc.)
- Aromatic hydrocarbon solvents (toluene, xylene)
- White spirit

Dilutions of from 1:1 to 1:9 are possible (Dilution of **Protectosil**® 100 NK and solvent)

* recommended solvent

Suitable porous, mineral substrates:

- Concrete (fresh or carbonated)
- Clinker masonry
- Ceramic tiles
- Sand-limestone
- Natural stone
- Cement render

Product Characteristics

- solvent-free
- low volatility
- high reactivity
- very good beading effect
- water vapor permeable, colorless impregnation
- seals hairline cracks up to 0.3 mm
- considerably reduces absorption of water and damaging water-borne salts (e.g. chlorides)
- very good penetration capacity
- very high alkali resistance
- stops the alkali-silica reaction

The substrates to be treated should be air-dry and clean in order to ensure deep penetration of the active ingredient. During application, the outside temperature and the temperature of the substrate should be in the range from 0 °C to 40 °C. The material should not be applied if there is strong wind or if it is raining. **Protectosil**® 100 NK must not come into contact with water either before or during use.

Protectosil® 100 NK must be applied by flow coating to the saturation point. This is achieved by allowing it to flow without pressure against the surface to be treated. All liquid delivery devices are suitable (airless spray guns, for example). The material must not be atomized.

Protectosil® 100 NK must remain in contact with the substrate for several seconds as a liquid film. Horizontal surfaces should have a shiny, wet appearance for 3-5 seconds. Vertical surfaces should exhibit a 30-50 cm shiny curtain of liquid.

Application

All equipment and containers must be clean and dry. After use, they can be cleaned with any organic solvent (methylated spirit, petrol or thinners).

Non-absorbent substrates such as window frames, window sills, plastic fittings, window glass, etc., should be covered before application. Surfaces which accidentally come into contact with **Protectosil**® 100 NK can be cleaned with alcohol (spirit) or aqueous soap solution (the compatibility with the surface in question should be checked in advance). Cleaning should be carried out as quickly as possible (within a few hours), otherwise formation of a silicone resin film can make cleaning more difficult. Silicone resin films which have formed are best removed using ethanol (spirit).

Plants in the region of the surfaces to be treated should be protected against contact with **Protectosil**® 100 NK. **Protectosil**® 100 NK reacts with the interfaces in pores and capillaries of the mineral surface and forms invisible, water-repellent interfacial compounds. However, since it is frequently unknown whether the material has been previously treated, and the exact type of treatment, a test should always be performed on a small area to make sure that no undesired secondary phenomena occur.

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. EVONIK DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, AND SHALL HAVE NO LIABILITY FOR, MERCHANTABILITY OF THE PRODUCT OR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE), OR OTHERWISE. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

Europe / Middle-East / Africa / Row

Evonik Industries AG

Inorganic Materials
Rodenbacher Chaussee 4
63457 Hanau-Wolfgang
Germany
PHONE +49 6181 59 13636
FAX +49 6181 59 13737
protectosil@evonik.com
www.protectosil.com

Asia / Pacific

Evonik Degussa (SEA) Pte. Ltd.

Inorganic Materials
3 Internatioanl Business Park
#07-18, Nordic European Centre
Singapore 609927
PHONE +65 6890 6830
FAX +65 6899 6630
protectosil@evonik.com
www.protectosil.com

Asia / Pacific

Evonik Taiwan Ltd.

Inorganic Materials
Artist Construction Bldg
9F, No. 133
Min Sheng East Road, Sec 3
Taipei, 105 Taiwan, R.O.C.
Taiwan
PHONE +886 227 17 1242
FAX +886 227 17 2106
protectosil@evonik.com
www.protectosil.com

North America

Evonik Degussa Corporation

Inorganic Materials
P.O. Box 677
299 Jefferson Road
Parsippany, NJ 07054-0677
USA
PHONE (TOLL FREE) +1 800 828 0919
PHONE +1 973 929 8513
FAX +1 973 929 8503
protectosil@evonik.com
www.protectosil.com

Asia / Pacific

Evonik Degussa (Shanghai) Co. Ltd.

Inorganic Materials
55, Chungdong Road
Shanghai 201108
P.R. China
PHONE +86 21 6119 1053
FAX +86 21 6119 1075
protectosil@evonik.com
www.protectosil.com

Asia / Pacific

Evonik Japan Co. Ltd

Inorganic Materials
12th Floor Monolith Building
2-3-1, Nishi-Shinjuku-ku
Tokyo 163-0912
Japan
PHONE +81 353 23 7300
FAX +81 353 23 7399
protectosil@evonik.com
www.protectosil.com

Latin America

Evonik Brasil Ltda.

Inorganic Materials
Alameda Campinas, 579
01404-000 São Paulo-SP
Brazil
PHONE +55 11 3146 4123
FAX +55 11 3146 4148
protectosil@evonik.com
www.protectosil.com

Asia / Pacific

Evonik Korea Ltd.

Inorganic Materials
94, Galsan 1-dong
Bupyeong-gu
Incheon, 403-081, Korea
PHONE +82 32 510 2433
FAX +82 32 505 2510
protectosil@evonik.com
www.protectosil.com

Asia / Pacific

Evonik India Pvt. Ltd.

Inorganic Materials
Krislon House
Saki Vihar Road, Anderi (E)
Mumbai - 400 072
India
PHONE +91 226 7238 809
FAX +91 226 7238 811
protectosil@evonik.com
www.protectosil.com