

# Protectosil® 266

## Silane water-repellent for masonry.

### Technical Data

Properties and test methods	Value	Unit	Method
Flash point	> 63	°C	EN 22719
Active ingredient content	> 97	%	-
Density (20°C)	1.035	g/cm <sup>3</sup>	DIN 51757
Appearance	clear, colorless to yellow liquid	-	-
Solvent	solvent-free	-	-
Viscosity	35	mPa.s	DIN 53015

### Registration

#### Protectosil® 266

EINECS/ELINCS (EU):	Yes
AICS (Australia):	No
DSL/NDSL (Canada):	*
PICCS (Philippines):	Yes
TSCA (USA):	Yes
IECS (P.R. China):	*
ENCS (Japan):	Yes
ECL (South Korea):	Yes
* = Information upon request	

Silane water-repellent for masonry.

**Protectosil® 266** is a free-flowing colorless to slightly yellow, frost resistant liquid based on a silane/ siloxane. **Protectosil® 266** can be applied at full-strength or after dilution with suitable solvents, such as ethanol or white spirit.

### Safety and Handling

Before considering the use of Dynasylan® and Protectosil® products please read its Material Safety Data sheet (MSDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Material Safety Data Sheet is available after registration on our website [www.dynasylan.com](http://www.dynasylan.com) or upon request from your local representative, customer service or from Evonik Industries AG, Product Safety Department, E-MAIL [sds-im@evonik.com](mailto:sds-im@evonik.com).

### Packaging and Storage

Provided that moisture is excluded, **Protectosil® 266** has a shelf life of two years if stored in originally sealed containers.

**Protectosil® 266** is supplied in 24 l PE canisters and 192 l plastic lined steel drums and 913 l bulk containers. The material should be stored at temperatures between -10° C and 40° C.

## Properties and Use

For waterproofing absorbent mineral facade construction materials such as:

- plaster facades
- sand-lime brickwork
- brickwork
- autoclaved aerated concrete
- cement fiber board

The substrates to be treated should be air-dry and clean in order to ensure deep penetration of the active ingredient. During application the outside temperature and the temperature of the substrate should be within the range from 5 to 40 °C. The material should not be applied if there is a strong wind or if it is raining. The material must not come into contact with water either before or during use. **Protectosil® 266** can be applied at full-strength or after dilution with suitable solvents. We recommend a minimum application concentration of 20% by weight (which corresponds to 1 part **Protectosil® 266** and 4 parts solvent).

### Product Characteristics:

- watervaporpermeable, colorless impregnation
- not film-forming
- effective on hairline cracks up to 0.3 mm
- good reduction of the water absorption
- good penetration
- suitable as a primer for facade topcoat
- frost resistant

## Application

Suitable solvents are:

- Ethanol water free\* (denatured with petroleum hydrocarbons)
- Aliphatic hydrocarbon solvents (pentane, hexane, heptane, etc.)
- Aromatic hydrocarbon solvents (toluene, xylene)
- White spirit

\* highly recommended solvent

The amount to be applied depends to a large extent on how absorbent the substrate is. The exact amount to be applied must be determined by a trial application. Typical product consumptions are >180 g/m<sup>2</sup> for concrete, >210g/m<sup>2</sup> for sand limestone and > 240g/m<sup>2</sup> and more for brick. In order to reach these consumption rates it might be necessary to apply the material in several steps. The prepared solution of **Protectosil® 266** must be applied by flowcoating to the saturation point. This is achieved by allowing it to flow without pressure against the surface to be treated. All liquid delivery devices are suitable (airless sprayguns, for example). The material must not be atomized or applied with a brush.

## Processing

The prepared solution of **Protectosil® 266** must remain in contact with the substrate for several seconds as a liquid film. Horizontal surfaces should have a shiny, wet appearance for 3-5 seconds. Vertical surfaces should exhibit a 30-50 cm shiny curtain of liquid. All equipment and containers must be clean and dry. After use they can be cleaned with any organic solvent (methylated spirit, petrol or thinners). Non-absorbent substrates such as glass, wood, plastic and metal cannot be treated with the prepared solution of **Protectosil® 266**. In the worst case, the product not absorbed by the substrate may react with atmospheric moisture to form a greasy, glossy silicone resin film. Substrates such as mentioned above should be covered before application. If they nevertheless become contaminated, the resulting film can be easily removed if cleaned immediately using conventional cleaning agents, or alcohol (spirit of soap) in difficult cases. Glass, wood and metal are not attacked by the prepared solution of **Protectosil® 266**. Neither are most plastics used in construction. If in doubt, carry out a preliminary test. Plants in the vicinity of the substrate to be treated should be protected against contact with the solution.

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. EVONIK DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, AND SHALL HAVE NO LIABILITY FOR, MERCHANTABILITY OF THE PRODUCT OR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE), OR OTHERWISE. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

#### **Europe / Middle-East / Africa / Row**

##### **Evonik Industries AG**

Inorganic Materials  
Rodenbacher Chaussee 4  
63457 Hanau-Wolfgang  
Germany  
PHONE +49 6181 59 13636  
FAX +49 6181 59 13737  
protectosil@evonik.com  
www.protectosil.com

#### **Asia / Pacific**

##### **Evonik Degussa (SEA) Pte. Ltd.**

Inorganic Materials  
3 Internatioanl Business Park  
#07-18, Nordic European Centre  
Singapore 609927  
PHONE +65 6890 6830  
FAX +65 6899 6630  
protectosil@evonik.com  
www.protectosil.com

#### **Asia / Pacific**

##### **Evonik Taiwan Ltd.**

Inorganic Materials  
Artist Construction Bldg  
9F, No. 133  
Min Sheng East Road, Sec 3  
Taipei, 105 Taiwan, R.O.C.  
Taiwan  
PHONE +886 227 17 1242  
FAX +886 227 17 2106  
protectosil@evonik.com  
www.protectosil.com

#### **North America**

##### **Evonik Degussa Corporation**

Inorganic Materials  
P.O. Box 677  
299 Jefferson Road  
Parsippany, NJ 07054-0677  
USA  
PHONE (TOLL FREE) +1 800 828 0919  
PHONE +1 973 929 8513  
FAX +1 973 929 8503  
protectosil@evonik.com  
www.protectosil.com

#### **Asia / Pacific**

##### **Evonik Degussa (Shanghai) Co. Ltd.**

Inorganic Materials  
55, Chungdong Road  
Shanghai 201108  
P.R. China  
PHONE +86 21 6119 1053  
FAX +86 21 6119 1075  
protectosil@evonik.com  
www.protectosil.com

#### **Asia / Pacific**

##### **Evonik Japan Co. Ltd**

Inorganic Materials  
12th Floor Monolith Building  
2-3-1, Nishi-Shinjuku-ku  
Tokyo 163-0912  
Japan  
PHONE +81 353 23 7300  
FAX +81 353 23 7399  
protectosil@evonik.com  
www.protectosil.com

#### **Latin America**

##### **Evonik Brasil Ltda.**

Inorganic Materials  
Alameda Campinas, 579  
01404-000 São Paulo-SP  
Brazil  
PHONE +55 11 3146 4123  
FAX +55 11 3146 4148  
protectosil@evonik.com  
www.protectosil.com

#### **Asia / Pacific**

##### **Evonik Korea Ltd.**

Inorganic Materials  
94, Galsan 1-dong  
Bupyeong-gu  
Incheon, 403-081, Korea  
PHONE +82 32 510 2433  
FAX +82 32 505 2510  
protectosil@evonik.com  
www.protectosil.com

#### **Asia / Pacific**

##### **Evonik India Pvt. Ltd.**

Inorganic Materials  
Krislon House  
Saki Vihar Road, Anderi (E)  
Mumbai - 400 072  
India  
PHONE +91 226 7238 809  
FAX +91 226 7238 811  
protectosil@evonik.com  
www.protectosil.com