

Protectosil® WS 600

Aqueous emulsion for the water repellent treatment of mineral porous materials, especially facades. Essentially VOC free.

Technical Data

Properties and test methods	Value	Unit	Method
Density (20 °C)	approx. 1,017	g/cm ³	DIN 51757
Appearance	white liquid	-	-
Flash point	> 90	°C	EN 22719
Viscosity (20 °C)	approx. 20	mPa.s	DIN 53015
Active ingredient	50	%	-

Registration

Protectosil® WS 600

EINECS/ELINCS (EU):	Yes
AICS (Australia):	No
DSL/NDSL (Canada):	*
PICCS (Philippines):	Yes
TSCA (USA):	Yes
IECSC (P.R. China):	*
ENCS (Japan):	Yes
ECL (South Korea):	No
*= Information upon request	

Aqueous emulsion for the water repellent treatment of mineral porous materials, especially facades. Essentially VOC free.

Safety and Handling

Before considering the use of **Protectosil®** products please read its Material Safety Data sheet (MSDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Material Safety Data Sheet is available after registration on our website www.dynasytan.com or upon request from your local representative, customer service or from Evonik Industries AG, Product Safety Department, E-MAIL sds-im@evonik.com.

Packaging and Storage

Protectosil® WS 600 is supplied in 25 l PE-containers, 200 l steel drums with PE-inliner and 1.000 l containers. **Protectosil®** WS 600 is not frost resistant and should not be stored at temperatures below 3 °C. Only demineralized water should be used for dilutions. **Protectosil®** WS 600 should be stored at temperatures between 3 °C and 40 °C. **Protectosil®** WS 600 has a shelf life of 12 months if properly stored in originally sealed containers.

Properties and Use

Protectosil® WS 600

- is suited for the water repellent impregnation of porous mineral substrates
- does not form sticky silicone films
- shows very good penetration on absorbent mineral materials
- gives water vapor permeable, colorless protection
- reduces significantly the uptake of water
- repels water soluble pollutants
- effective on micro cracks of up to 0.3 mm
- can be diluted with water
- is very efficient on mineral rendering, sand-lime brickwork, hard-baked brickwork, roofing tiles

We recommend using a minimum concentration of 10% of the active ingredient in water. This corresponds to a dilution with water (preferable demineralized water) of 1:4. **Protectosil® WS 600** is not recommended to be applied undiluted. Minimum dilution rate should be 1:1.

The concentration to be used and the exact amount to be applied are depending on the absorbance of the substrate.

The substrates to be treated should be dry and clean. Acceptable surface cleaning methods include sandblasting and water blasting.

During application outside temperatures and surface temperatures should be between 5 °C and 40 °C. **Protectosil® WS 600** should not be applied during strong wind or rain.

Protectosil® WS 600 should be applied by wet-on-wet flow coating to the saturation point. The solution should be applied in 2 - 3 coats without drying between the coats. On vertical surfaces the solution should run down in the form of a clearly visible descending wet curtain. This is achieved by allowing the solution to flow against the surface of the building material without pressure. Most liquid delivery devices e.g. airless pumping equipment are suitable. The material should not be atomized or applied with a brush.

The water repellent effect of **Protectosil® WS 600** can develop within minutes or require up to several days depending on the substrate and weather conditions. Therefore, the impregnation should be applied continuously and without a break to avoid overlapping.

Non-absorbent substrates such as window frames, window sills, plastic fittings, window glass, etc., should be covered before application. Surfaces which accidentally come into contact with **Protectosil® WS 600** can be cleaned with alcohol (spirit) or aqueous soap solution. Cleaning should be carried out as quickly as possible (within a few hours), otherwise formation of a silicone resin film can make cleaning more difficult. Silicone resin films are best removed using ethanol (or spirit). Plant life should be protected from overspray.

Protectosil® WS 600 reacts with the interfaces in pores and capillaries of the mineral surface and forms invisible, waterrepellent interfacial compounds. To determine the exact amount to be applied and to check whether previous or following treatments are compatible with the **Protectosil® WS 600** treatment it is recommended to do a small test patch first.

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. EVONIK DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, AND SHALL HAVE NO LIABILITY FOR, MERCHANTABILITY OF THE PRODUCT OR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE), OR OTHERWISE. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

Europe / Middle-East / Africa / Row

Evonik Industries AG

Inorganic Materials
Rodenbacher Chaussee 4
63457 Hanau-Wolfgang
Germany
PHONE +49 6181 59 13636
FAX +49 6181 59 13737
protectosil@evonik.com
www.protectosil.com

Asia / Pacific

Evonik Degussa (SEA) Pte. Ltd.

Inorganic Materials
3 Internatioanl Business Park
#07-18, Nordic European Centre
Singapore 609927
PHONE +65 6890 6830
FAX +65 6899 6630
protectosil@evonik.com
www.protectosil.com

Asia / Pacific

Evonik Taiwan Ltd.

Inorganic Materials
Artist Construction Bldg
9F, No. 133
Min Sheng East Road, Sec 3
Taipei, 105 Taiwan, R.O.C.
Taiwan
PHONE +886 227 17 1242
FAX +886 227 17 2106
protectosil@evonik.com
www.protectosil.com

North America

Evonik Degussa Corporation

Inorganic Materials
P.O. Box 677
299 Jefferson Road
Parsippany, NJ 07054-0677
USA
PHONE (TOLL FREE) +1 800 828 0919
PHONE +1 973 929 8513
FAX +1 973 929 8503
protectosil@evonik.com
www.protectosil.com

Asia / Pacific

Evonik Degussa (Shanghai) Co. Ltd.

Inorganic Materials
55, Chungdong Road
Shanghai 201108
P.R. China
PHONE +86 21 6119 1053
FAX +86 21 6119 1075
protectosil@evonik.com
www.protectosil.com

Asia / Pacific

Evonik Japan Co. Ltd

Inorganic Materials
12th Floor Monolith Building
2-3-1, Nishi-Shinjuku-ku
Tokyo 163-0912
Japan
PHONE +81 353 23 7300
FAX +81 353 23 7399
protectosil@evonik.com
www.protectosil.com

Latin America

Evonik Brasil Ltda.

Inorganic Materials
Alameda Campinas, 579
01404-000 São Paulo-SP
Brazil
PHONE +55 11 3146 4123
FAX +55 11 3146 4148
protectosil@evonik.com
www.protectosil.com

Asia / Pacific

Evonik Korea Ltd.

Inorganic Materials
94, Galsan 1-dong
Bupyeong-gu
Incheon, 403-081, Korea
PHONE +82 32 510 2433
FAX +82 32 505 2510
protectosil@evonik.com
www.protectosil.com

Asia / Pacific

Evonik India Pvt. Ltd.

Inorganic Materials
Krislon House
Saki Vihar Road, Anderi (E)
Mumbai - 400 072
India
PHONE +91 226 7238 809
FAX +91 226 7238 811
protectosil@evonik.com
www.protectosil.com